



آتش پاد سازه ایرانیان  
Atash Pad Sazeh Iranian

Promat



Tehran Office Tel/Fax: +98 21 2211 8391  
South Pars Office Tel/Fax: +98 77 3721 4698  
www.apsi.ir / www.apsi-co.com  
info@apsi.ir

# CAFCO® PSK 101

Sealer & Keycoat

petrochemical applications



For use with Cafco FENDOLITE® MII Vermiculite Cement Based Wet Mix Spray

[www.promat-spray.com](http://www.promat-spray.com)

## CAFCO® PSK 101

### Sealer & Keycoat

#### INTRODUCTION

CAFCO® PSK 101 is a single pack, multi purpose synthetic latex, water based emulsion for use as a sealer and keycoat as a component of the Cafco FENDOLITE® integrated fire protectivecoating system.

CAFCO® PSK 101 is suitable for on site or off site application to construction elements such as steel or concrete sections and metal decks.

Onshore oil and gas, petrochemical and power industries will benefit from the use of CAFCO® PSK 101.

Properties and performance	
Colour and finish	Dark green (nearest to BS 4800: 1981, colour code 10 B 25). May be applied by spray, roller or brush
Typical thickness	100-150 microns wet film thickness (WFT) Do not apply less than 100 microns 55-82 microns dry film thickness (DFT)
Practical coverage	Dependent on surface texture, substrate porosity, application method and technique
Theoretical coverage	8m <sup>2</sup> /litre at 125 microns WFT
Number of coats	One or more as required dependent on application technique. May be recoated once previous coat is touch dry
Maximum over coating time	2 months with either more CAFCO® PSK 101 or Cafco FENDOLITE® MII
Cure	By air drying
Drying time	Touch dry ½ to 1 hour at 20°C and RH 50% Fully dry 2 to 6 hours at 20°C and RH 50% The drying time will vary with ambient conditions, but high humidity, low temperature and low air change will hinder cure significantly
Solids by weight	55%
Weight	1.25kg/litre

#### ADVANTAGES

Strongly bonded coating system.

#### QUALITY ASSURANCE

Promat operates a quality system in accordance with BS EN ISO 9001: 2000 and has received full accreditation to these standards.

Operating to these standards means that all activities, which have a bearing upon quality, are set out in written procedures.

Systematic and thorough checks are made on all materials and their usage. Test equipment is subjected to regular checks and is referred back to national standards.

The information given in this data sheet is based on actual tests and is believed to be typical of the product. No guarantee of results is implied however, since conditions of use are beyond our control.



# CAFCO® PSK 101

## Sealer & Keycoat

Preparation	
Typical substrates	Unprimed or primed steel
Substrate preparation	The substrate must be clean, dry and free from dust, loose millscale, loose rust, oil, visible moisture (including condensation) and any other condition preventing good adhesion
Application	
Initial steps	Stir contents before use. Do not thin
Methods	CAFCO® PSK 101 may be applied with an industrial type airless or air-assisted spray, or lambswool roller. It may also be applied with a brush in small (maximum 1m <sup>2</sup> ) areas only
Limitations	CAFCO® PSK 101 may be applied when the substrate and air temperatures are at least 2°C and rising. Maximum air and substrate temperature is 45°C Substrate temperature should be at least 2°C above dew point temperature Protect from rain, hail etc until dry

### PACKAGING

20 litre metal pails.

### STORAGE

Protect from frost, excessive heat (above 45°C) and strong radiant sunlight.

### SHELF LIFE

Maximum 6 months.

### ENVIRONMENTAL

Do not discharge into drains, watercourses or soil.

### HEALTH AND SAFETY

Adequate ventilation must be provided during use. Avoid contact with the skin and eyes by using eye protection, gloves, barrier cream and a face mask.

If the product comes into contact with the skin, wash immediately with soap and water. If the eyes are affected, flush with plenty of water and seek medical attention immediately.

A safety data sheet is available from Promat upon request.

Promat activities are conducted with due regard to all statutory requirements with appropriate safeguards against exposing employees and the public to health and safety risks.

## HEAD OFFICE, BELGIUM

**Promat International N.V.**  
Bormstraat 24  
2830 Tiselt  
Tel: +32 15 718 100  
Fax: +32 15 718 109  
Email: info@promat  
international.com  
www.promat-international.com  
www.promat-tunnel.com  
www.promat-marine.com  
www.promat-spray.com

## ASIA PACIFIC HEADQUARTERS, MALAYSIA

**Promat International (Asia Pacific) Limited**  
Unit 19-02-01  
Level 2 PNB Damansara  
No.19 Lorong Dungun  
Damansara Heights  
50490 Kuala Lumpur  
Tel: +60 3 2095 5111  
Fax: +60 3 2095 6111  
Email: spraysinfo@promat-ap.com  
www.promat-ap.com

## AUSTRALIA

**Promat Australia Pty. Limited**  
1 Scotland Road, Mile End South  
SA 5031 Adelaide  
Tel: 1800 PROMAT  
Fax: +61 8 8352 1014  
Email: spraysinfo@promat.com.au  
www.promat-ap.com

**Promat Australia Pty. Limited**  
Unit 1, 175 Briens Road  
NSW 2152 Northmead  
Tel: 1800 PROMAT  
Fax: +61 2 9630 0258  
Email: spraysinfo@promat.com.au  
www.promat-ap.com

**Promat Australia Pty. Limited**  
3/273 Williamstown Road  
VIC 3207 Port Melbourne  
Tel: 1800 PROMAT  
Fax: +61 3 9645 3844  
Email: spraysinfo@promat.com.au  
www.promat-ap.com

## AUSTRIA

**Promat Ges.m.b.H.**  
Seybelgasse 13  
1230 Wien  
Tel: +43 1 865 4501  
Fax: +43 1 865 3600  
Email: office@promat.at  
www.promat.at

## BELGIUM

**Promat N.V.**  
Kuiermansstraat 1  
1880 Kapelle-op-den-Bos  
Tel: +32 15 713 351  
Fax: +32 15 718 229  
Email: info@promat.be  
www.promat.be

## CHINA

**Promat China Limited**  
Room 503, Block B, Qi Lin Plaza  
13-35 Pan Fu Road  
510180 Guangzhou  
Tel: +86 20 8136 1167  
Fax: +86 20 8136 1372  
Email: spraysinfo@promat-ap.com  
www.promat.com.cn

**Promat North China (Division of Promat China Limited)**  
Room 1507 Building 5  
SOHO Xiandaicheng  
No.88 Jianguo Road  
Chaoyang District  
100022 Beijing  
Tel: +86 10 8589 1254  
Fax: +86 10 8589 2904  
Email: spraysinfo@promat-ap.com  
www.promat.com.cn

## CZECH REPUBLIC

**Promat s.r.o.**  
Kkalova 22/784  
16000 Praha 6 - Bubeneč  
Tel: +420 2 2439 0811  
Fax: +420 2 3333 3576  
Email: promat@promatpraha.cz  
www.promatpraha.cz

## DENMARK

**Promat ApS**  
Tåstrup Stationscenter  
Selsmosevej 2, 1. floor  
2630 Tåstrup  
Tel: +45 7020 0482  
Fax: +45 7020 0483  
Email: info@promat-nordic.com  
www.promat-nordic.com

## FRANCE

**Promat S.A.S.**  
BP 66 Rue de L'Ammandier  
78540 Vernouillet  
Tel: +33 1 3979 6160  
Fax: +33 1 3971 1660  
Email: info@promat.fr  
www.promat.fr

## GERMANY

**Promat GmbH**  
Scheifenkamp 16  
40878 Ratingen  
Tel: +49 2102 493 0  
Fax: +49 2102 493 111  
Email: mail@promat.de  
www.promat.de

## HONG KONG

**Promat International (Asia Pacific) Limited**  
Room 1010, C.C. Wu Building  
302-308 Hennessy Road  
Wanchai  
Tel: +852 2836 3692  
Fax: +852 2834 4313  
Email: spraysinfo@promat-ap.com  
www.promat.com.hk

## INDIA

**Promat International (Asia Pacific) Limited (India Representative Office)**  
610-611, Ansal Imperial Tower  
C-Block, Community Centre  
Naraina Vihar, Naraina  
110028 New Delhi  
Tel: +91 11 2577 8413  
Fax: +91 11 2577 8414  
Email: spraysinfo@promat-ap.com  
www.promat-ap.com

## ITALY

**Promat S.p.A.**  
Corso Paganini 39/3  
16125 Genova  
Tel: +39 010 248 8411  
Fax: +39 010 213 768  
Email: info@promat.it  
www.promat.it

## MALAYSIA

**Promat (Malaysia) Sdn. Bhd.**  
Unit 19-02-01  
Level 2 PNB Damansara  
No.19 Lorong Dungun  
Damansara Heights  
50490 Kuala Lumpur  
Tel: +60 3 2095 8555  
Fax: +60 3 2095 2111  
Email: spraysinfo@promat-ap.com  
www.promat-ap.com

## NETHERLANDS

**Promat B.V.**  
Vleugelboot 22  
3991 CL Houten  
Tel: +31 30 241 0770  
Fax: +31 30 241 0771  
Email: info@promat.nl  
www.promat.nl

## POLAND

**Promat TOP Sp. z o.o.**  
ul. Przeclawska 8  
03 879 Warszawa  
Tel: +48 22 212 2280  
Fax: +48 22 212 2290  
Email: top@promatop.pl  
www.promatop.pl

## RUSSIA

**Promat GmbH**  
Repräsentanz  
ul. Kanternirovskaya 58  
115477 Moscow  
Tel: +7 495 325 4268  
Fax: +7 495 231 7977  
Email: gd@promat.ru  
www.promat.ru

## SINGAPORE

**Promat Building System Pte. Limited**  
10 Science Park Road  
#03-14 The Alpha  
Singapore Science Park II  
117684 Singapore  
Tel: +65 6776 7635  
Fax: +65 6776 7624  
Email: spraysinfo@promat-ap.com  
www.promat-ap.com

## SPAIN

**Promat Ibérica S.A.**  
C/ Velazquez, 41 - 2 Planta  
28001 Madrid  
Tel: +34 91 781 1550  
Fax: +34 91 575 1597  
Email: info@promat.es  
www.promat.es

## SWITZERLAND

**Promat AG**  
Stationsstrasse 1  
8545 Rickenbach-Sulz  
Tel: +41 52 320 9400  
Fax: +41 52 320 9402  
Email: office@promat.ch  
www.promat.ch

## UNITED ARAB EMIRATES

**Promat Middle East**  
Suite 1805, Floor 18  
Festival City Tower  
P O. Box 123945, Dubai  
Tel: +971 4 232 9780  
Fax: +971 4 232 9781  
Email: promatmiddleeast@promat.co.uk  
www.promat-spray.com

## UNITED KINGDOM

**Promat UK Limited**  
The Sterling Centre  
Eastern Road, Bracknell  
RG12 2TD Berkshire, Great Britain  
Tel: +44 1344 381 300  
+44 1344 381 400 (technical)  
Fax: +44 1344 381 301  
Email: marketinguk@promat.co.uk  
www.promat-spray.com

**Promat Ireland**  
43 Fitzwilliam Square  
Dublin 2, Ireland  
Tel: +353 1 6765778  
www.promat.ie

## VIETNAM

**Promat International (Asia Pacific) Limited (Vietnam Representative Office)**  
Room 606 Giay Viet Plaza  
180-182 Ly Chinh Thang Street  
Ward 9, District 3  
Hochiminh City  
Tel: +84 904 055 055  
Fax: +84 8 931 5964  
Email: spraysinfo@promat-ap.com  
www.promat-ap.com